

PRODUCT DESCRIPTION

Stonclad GR is an environmentally friendly four-component, troweled, epoxy mortar system utilizing recycled materials and rapidly renewable soy based components. The system utilizes 25% recycled glass blended with an epoxy resin, amine curing agent and soy based additives. Stonclad GR can be applied at thickness ranging from 1/8 in./3 mm to 1/4 in./6 mm depending on application requirements. Stonclad GR cures to an extremely hard, impact resistant surface which exhibits excellent abrasion, wear and chemical resistance.

SYSTEM OPTIONS

Coatings

To improve cleanability and increase the resistance to damage from abrasion and chemical spillages, the following coatings are recommended: Stonkote GS4, Stonkote HT4.

Waterproofing

Where the total system must be waterproof, use of Stonhard's Stonproof ME7 membrane system is required, with strict adherence to application instructions.

Cove Base

To provide for an integral seal at the joint between the floor and the wall, cove bases in heights from 2 to 6 in./5 to 15 cm may be specified.

Fiberglass Reinforcement

To provide additional surface strength to the system, a surface veil of fiberglass reinforcement should be installed for areas exposed to instantaneous temperature changes of greater than 100°F/38°C.

PACKAGING

Stonclad GR is packaged in units for easy handling. Each unit consists of:

- 2 cartons, each containing:
 - 6 foil bags of Amine
 - 6 poly bags of Resin

12 individual bags of aggregate

- 1 carton containing:
 - 12 bags of pigment

COVERAGE

Each unit of Stonclad GR will cover approximately 200 sq. ft./18.58 sq. m of surface at a nominal 1/4 in./6 mm thickness.

STORAGE CONDITIONS

Store all components of Stonclad GR between 60 to 85°F/16 to 30°C in a dry area. Avoid excessive heat and do not freeze. The shelf life is 3 years in the original, unopened container.

COLOR

Stonclad GR is available in 12 standard colors. Refer to the Stonclad Color Sheet.

SUBSTRATE

Stonclad GR, with the appropriate primer, is suitable for application over concrete, wood, brick, quarry tile, metal or Stonhard Stonset grouts. For questions regarding other possible substrates or an appropriate primer, contact your local Stonhard representative or Technical Service.

SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or Technical Service.

PRIMING

The use of Standard Primer is necessary for all applications of Stonclad GR over all substrates except Stonset grouts. Over Stonset grouts, Stonhard's Stonset Primer is used. Please see the appropriate primer Product Data sheet for details.

PHYSICAL CHARACTERISTICS

Compressive Strength	10,000 psi
(ASTM C-579).....	after 7 days
Tensile Strength.....	1,750 psi
(ASTM C-307)	
Flexural Strength.....	4,000 psi
(ASTM C-580)	
Flexural Modulus of Elasticity	2.0 x 10 ⁶ psi
(ASTM C-580)	
Hardness	85 to 90
(ASTM D-2240, Shore D)	
Impact Resistance	>160 in./lbs.
(ASTM D-2794)	
Abrasion Resistance	0.1 gm max. weight loss*
(ASTM D-4060, CS-17)	
Flammability.....	Class 1
(ASTM E-648)	
Thermal Coefficient of	
Linear Expansion	11 x 10 ⁻⁶ in./in.°F
(ASTM C-531)	
Water Absorption	0.2%
(ASTM C-413)	
Cure Rate	24 hours for normal operations
(at 75°F/25°C)	
VOC Content.....	<5 g/L
(ASTM D-2369)	

* Test samples finished with one coat of high solids epoxy coating

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field applied materials may vary and certain test methods can only be conducted on lab made test coupons.

MIXING

- Proper mixing is critical for the product to exhibit the proper application properties, cure properties and ultimate physical properties.
- Mechanical mixing using a JB Blender (or equivalent 5 gal. pail mixer) or a larger mortar mixer (e.g., a Baugh 3 Batch Mixer) is required.
- See Stonclad GR Directions for further details.

APPLYING

- DO NOT attempt to install material if the temperature of Stonclad GR components and substrate are not within 60 to 85°F/16 to 30°C. The cure time and application properties of the material are severely affected at temperatures outside of this range.
- Material must be applied immediately after mixing.
- A suitable screed applicator is used to distribute the mixed Stonclad GR onto the floor.
- Steel finishing trowels are used to compact and smooth the surface of the material to the required thickness.
- Detailed application instructions can be found in the Stonclad GR Directions.

NOTES

- Procedures for maintenance of the flooring system during operations are described in the Stonkleen Floor Cleaning Procedures Brochure.
- Specific information regarding chemical resistance is available in the Stonclad Chemical Resistance Guide.
- Safety Data Sheets for Stonclad GR are available on line at www.stonhard.com under Products or upon request.
- A staff of technical service engineers is available to assist with installation or to answer questions related Stonhard's flooring products.
- Requests for technical service or literature can be made through local sales representatives and offices, or corporate offices located worldwide.
- The appearance of all floor, wall and lining systems will change over time due to normal wear, abrasion, traffic and cleaning. Generally, high gloss coatings are subject to a reduction in gloss, while matte finish coatings can increase in gloss level under normal operating conditions.
- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly and deep cleaned periodically to ensure no contaminant buildup occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require traction-enhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use.

IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

06/19
© 2019 Stonhard www.stonhard.com

STONHARD®

USA HQ	(800) 257 7953	Mexico	+ (52) 55 9140 4500	Belgium	+ (32) 67 49 37 10	South Africa	+ (27) 11 254 5500	Australia	+ (61) 3 9587 7433
Canada	(800) 263 3112	Argentina	+ (54) 11 5032 3113	Dubai, UAE	+ (971) 4 3470460	China	+ (86) 21 61838698	India	+ (91) 22 28500321