

PRODUCT DESCRIPTION

Stonres RTZ-2 is a nominal 3/16 in./5 mm resilient urethane flooring system. This easy-to-clean, seamless, resilient system shares many of the same qualities of Stonres RTZ, such as exceptional acoustic efficiency and ergonomic comfort, but provides a different, more natural look, similar to terrazzo. The system combines superior aesthetics with excellent wear and stain resistance, offering progressive design options. It is comprised of:

Note: This product is recommended for front of house areas and anywhere terrazzo may be implemented.

Stonres RTZ Mortar

A three-component, UV-resistant, resilient, urethane mortar consisting of urethane resin, curing agent, and pigmented, translucent aggregate.

Stonres Groutcoat

A two-component, clear, UV-resistant, aliphatic, polyaspartic urethane grout coat.

Stonseal CF7

A two-component, non-reflective, high-performance, water-based, VOC-compliant polyurethane coating.

PACKAGING

Stonres RTZ-2 is packaged in units for easy handling. Each unit consists of:

Stonres RTZ Mortar

- 14 boxes, each containing:
 - 1 foil bag of Isocyanate
- (14) 5 gallon pails of Polyol
- 22 bags of Part C aggregate

Stonres Groutcoat

- (0.5) carton containing:
 - 1 poly bag of Isocyanate
- (1) 1 gallon can of Amine

Stonres Skim Coat

- 0.2 carton containing:
 - 1 can of Isocyanate
 - 1 can of Stonres RTZ Skim Coat Polyol
- 1 bag of Stonres RTZ Skim Coat Part C Aggregate

Stonseal CF7

- 1 carton containing:
 - 1 foil bag of Isocyanate
- (1) 1-gallon pail of Polyol

COVERAGE

Each unit of Stonres RTZ-2 will cover approximately 220 sq. ft./20.4 sq. m of surface at a nominal 3/16 in./5 mm finished thickness. A batch of Stonres RTZ-2 Base is made up of one foil bag of Isocyanate, one 5-gallon pail of Polyol, and one bag of Part C. When mixed, each batch will cover approximately 16 sq. ft./1.48 sq. m at the above thickness.

STORAGE CONDITIONS

Store all components of Stonres RTZ-2 from 65 to 85°F/18 to 30°C in a dry area. Avoid excessive heat and do not freeze. The shelf life of the Mortar is 3 years, all other components are one year in the original, unopened container. Do not store outdoors, in boiler rooms, compressor rooms, refrigerators, or near radiators, steam pipes, etc.

PHYSICAL CHARACTERISTICS

Tensile Strength	1200 psi (ASTM C-307)
Hardness.....	85 (ASTM D-2240, Shore A)
Percent Elongation	150% (ASTM D-638)
Impact Resistance	60 in./lbs. (ASTM D-2794)
Static Load Limit.....	0.002 in./0.05 mm (ASTMF-970)..... (125 lb./57 kg. load)
Resistance to Heat	Delta E <8 (ASTM F-1514)..... (7 days @ 158°F/70°C)
Residual Indentation.....	<1% thickness (ASTM F-1914)..... (140 lb./64 kg. load)
Abrasion Resistance.....	0.03 gm (ASTM D-4060 CS-17)
Thermal Coefficient of	3.3 x 10-5in./in. °F Linear Expansion (ASTM C-531)
Flammability	Class 1 (ASTM E-648)
Noise Reduction Coefficient.....	0.05 (ASTM C-423)
VOC Content.....	RTZ Mortar - 13 g/l (ASTM D-2369, Method E)..... Stonres Groutcoat - 90 g/l
	Stonseal CF7 - 47 g/l (Method C)
Cure Rate.....	12 hours for foot traffic (@77°F/25°C).....48 hours for normal operations

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field-applied materials may vary and certain test methods can only be conducted on lab-made test coupons.

COLOR

Stonres RTZ-2 is available in 12 standard colors. Refer to the Stonres RTZ-2 Color Sheet. Custom Colors are available upon request.

SUBSTRATE

Stonres RTZ-2 is suitable for application over properly prepared concrete, wood or steel surfaces. It is not recommended for use over asphalt, mastic, gypsum-based products, brick or painted surfaces. These must first be removed by mechanical means to expose the substrate prior to overlayment.

SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or Technical Service.

Note: A flat level substrate is required for Stonres RTZ-2 application and cannot be installed over a pitched surface.

PRIMING

The use of the Standard Primer/SL Primer priming system is required for all applications of RTZ over concrete or wood. Metal substrates must be primed immediately following preparation with HT primer.

The substrate must be free of voids and pinholes after priming and prior to the start of the mortar application and the primer layer must not be cured for longer than 24 hours to ensure proper intercoat adhesion.

MIXING

- Proper mixing is critical for the products to exhibit the proper application properties, cure properties and ultimate physical properties.
- Mechanical mixing is required for all components.
- See Stonres RTZ-2 Directions for further details.

APPLYING

- DO NOT attempt to install material if the temperature of the Stonres RTZ-2 components and substrate are not within 65 to 85°F/18 to 30°C. The cure time and application properties of the material are severely affected if the temperatures are outside of this range.
- Stonres RTZ-2 Mortar material is mixed just prior to use in accordance with prescribed directions. The base material is then screed rake applied or by hand with notched trowel. Additional Part C is broadcasted into the surface immediately after raking/troweling. The material is then spike rolled to help embed the chips as well as provide additional air release and leveling.
- After a minimum of 20 hours curing time, sand the surface of the RTZ Mortar using the recommended grit sandpapers.
- Squeegee apply and backroll Stonres Groutcoat with a medium nap roller.
- After 4 hours of minimum cure time, roller apply Stonseal CF7. After 12 hours of cure, inspect and apply Stonres RTZ Skim Coat as per the directions. Apply a second coat of Stonseal CF7. Allow a minimum of 12 hours of cure before foot traffic and 48 hours before washdown/cleaning procedures commence. (Reference the Stonseal CF7 Product Data for further details.)

Note: Two coats of Stonseal CF7 are required for all applications of Stonres RTZ-2.

Detailed application instructions can be found in the Stonres RTZ-2 Directions.

PRECAUTIONS

- Use these materials only in strict accordance with the manufacturer's recommended safety procedures. Dispose of waste materials in accordance with government regulations.
- The selection of proper protective clothing and equipment will significantly reduce the risk of injury. Body covering apparel, safety goggles or safety glasses, and impermeable gloves are required.
- In case of contact, flush area with water for 15 minutes and seek medical attention. Wash skin with soap and water.
- If material is ingested, immediately contact a physician. DO NOT INDUCE VOMITING.
- During prep-work of floor substrate or mixing of Stonhard product while adding aggregate, dust masks must be worn.

NOTES

- Procedures for maintenance of the flooring system during operations are described in the Stonkleen Floor Cleaning Procedures Brochure.
- Specific information regarding chemical resistance is available in the Stonres Chemical Resistance Guide.
- Safety Data Sheets for Stonres RTZ-2 are available online at www.stonhard.com under Products or upon request.
- A staff of technical service engineers is available to assist with installation or to answer questions related to Stonhard products.

- A NIOSH approved air purifying respirator (APR) equipped with organic vapor cartridges is required during application of the Stonres Groutcoat.
- Requests for technical service or literature can be made through local sales representatives and offices or corporate offices located worldwide.
- The appearance of all floor, wall and lining systems will change over time due to normal wear, abrasion, traffic, and cleaning. Generally, high-gloss coatings are subject to a reduction in gloss, while matte-finish coatings can increase in gloss level under normal operating conditions.
- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly and deep cleaned periodically to ensure no contaminant buildup occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require traction-enhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use.

IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

06/21
© 2021 Stonhard www.stonhard.com

STONHARD®

USA HQ	(800) 257 7953	Mexico	+(52) 55 9140 4500	Belgium	+(32) 67 49 37 10	South Africa	+(27) 11 254 5500	Australia	+(61) 3 9587 7433
Canada	(800) 263 3112	Argentina	+(54) 11 5032 3113	Dubai, UAE	+(971) 4 3470460	India	+(91) 22 28500321		